

SABIC Innovative Plastics Cycloy® CX7240U PC+ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Cycloy* CX7240U resin is an injection moldable PC/ABS blend with a UV stabilization package. It contains non-brominated and non-chlorinated flame retardant systems to meet thin wall flame resistance. Excellent flow and impact balance together with the thin wall flame resistance and all color options make Cycloy CX7240U an ideal candidate for a wide variety of thin wall applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-CX7240U-PCABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.100 %	0.100 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.20 %	0.20 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm @Thickness 3.20 mm	0.0040 - 0.0060 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	16 g/10 min @Load 2.16 kg, Temperature 260 °C	16 g/10 min @Load 4.76 lb, Temperature 500 °F	ASTM D1238
Melt Index of Compound	15 g/10 min @Load 2.16 kg, Temperature 260 °C	15 g/10 min @Load 4.76 lb, Temperature 500 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	65.0 MPa	9430 psi	Type I, 50 mm/min; ASTM D638
	65.0 MPa	9430 psi	50 mm/min; ISO 527
Elongation at Break	90 %	90 %	50 mm/min; ISO 527
	100 %	100 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	4.0 %	4.0 %	50 mm/min; ISO 527
	4.1 %	4.1 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.53 GPa	367 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric 2.93 GPa	English 425 ksi	Comments 50 mm/min; ASTM D638
Flexural Yield Strength	96.0 MPa	13900 psi	2 mm/min; ISO 178
	104 MPa	15100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.50 GPa	363 ksi	2 mm/min; ISO 178
	2.75 GPa	399 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	5.00 J/cm	9.37 ft-lb/in	ASTM D256
	1.00 J/cm @Temperature -30.0 °C	1.87 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Notched (ISO)	20.0 kJ/m ²	9.52 ft-lb/in ²	80*10*3; ISO 180/1A
	10.0 kJ/m ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	80*10*3; ISO 180/1A
Charpy Impact, Notched	2.00 J/cm ²	9.52 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.00 J/cm ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	65.0 J	47.9 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	62.0 µm/m-°C	34.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	62.5 µm/m-°C	34.7 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	53.5 µm/m-°C	29.7 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa	54.0 µm/m-°C	30.0 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	100 °C	212 °F	unannealed; ASTM D648

(56 psi) Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	93.0 °C	199 °F	Flatw 80*10*4 sp=64mm; ISO 75/ Af
	89.0 °C	192 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	99.0 °C	210 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	106 °C	223 °F	Rate B/50; ASTM D1525
	110 °C	230 °F	Rate B/50; ISO 306
	113 °C	235 °F	Rate B/120; ISO 306
UL RTI, Electrical	90.0 °C	194 °F	UL 746B
UL RTI, Mechanical with Impact	90.0 °C	194 °F	UL 746B
UL RTI, Mechanical without Impact	90.0 °C	194 °F	UL 746B
Flammability, UL94	V-2	V-2	UL 94
	@Thickness 0.400 mm	@Thickness 0.0157 in	
	V-1	V-1	UL 94
	@Thickness 0.600 mm	@Thickness 0.0236 in	
	V-0	V-0	UL 94
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	5VB	5VB	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	5VA	5VA	UL 94
	@Thickness 3.00 mm	@Thickness 0.118 in	
Glow Wire Test	800 °C	1470 °F	IEC 60695-2-13
	825 °C	1520 °F	IEC 60695-2-13
	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A

Electrical Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
Ball Pressure Test, 75°C +/- 2°C		PASS	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China