

SABIC Innovative Plastics Cycloy® FXC630SK PC+ABS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

PC+ABS, of non-chlorinated & non-brominated flame retardant with Sparkle effect. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-FXC630SK-PCABS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.60 % @Temperature 23.0 °C	0.60 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	on tensile bar; SABIC Method
Melt Flow	13 g/10 min @Load 2.16 kg, Temperature 260 °C	13 g/10 min @Load 4.76 lb, Temperature 500 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ISO 2039-2
Hardness, H358/30	116 MPa	16800 psi	ISO 2039-1
Tensile Strength at Break	40.0 MPa	5800 psi	5 mm/min; ISO 527
Tensile Strength, Yield	50.0 MPa	7250 psi	5 mm/min; ISO 527
Elongation at Yield	4.0 %	4.0 %	5 mm/min; ISO 527
Tensile Modulus	2.80 GPa	406 ksi	1 mm/min; ISO 527
Flexural Yield Strength	98.0 MPa	14200 psi	2 mm/min; ISO 178
Flexural Modulus	2.80 GPa	406 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ² @Temperature -30.0 °C	2.38 ft-lb/in ² @Temperature -22.0 °F	80*10*3; ISO 180/1A
	8.00 kJ/m ² @Temperature 23.0 °C	3.81 ft-lb/in ² @Temperature 73.4 °F	80*10*3; ISO 180/1A

Mechanical Properties	0.500 J/cm² Metric	2.38 ft-lb/in² English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.800 J/cm²	3.81 ft-lb/in²	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Taber Abrasion, mg/1000 Cycles	82	82	CS-17; SABIC Method
	@Load 1.00 kg	@Load 2.20 lb	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	75.0 µm/m-°C	41.7 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	75.0 µm/m-°C	41.7 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	ISO 8302
Hot Ball Pressure Test	<= 85.0 °C	<= 185 °F	IEC 60695-10-2
Vicat Softening Point	94.0 °C	201 °F	Rate B/50; ISO 306
	97.0 °C	207 °F	Rate B/120; ISO 306
UL RTI, Electrical	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical with Impact	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical without Impact	60.0 °C	140 °F	UL 746B
Flammability, UL94	V-2	V-2	UL 94
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	V-1	V-1	UL 94
	@Thickness 1.20 mm	@Thickness 0.0472 in	
	V-0	V-0	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	5VB	5VB	UL 94
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Oxygen Index	32 %	32 %	LOI; ISO 4589
Glow Wire Test	960 °C	1760 °F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00 \times 10^{15}$ ohm	$\geq 1.00 \times 10^{15}$ ohm	ROA; IEC 60093
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	2.8	2.8	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
	25.0 kV/mm	635 kV/in	in oil; IEC 60243-1
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	35.0 kV/mm	889 kV/in	in oil; IEC 60243-1
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Dissipation Factor	0.0040	0.0040	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.0080	0.0080	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Descriptive Properties	Value	Comments
Ball Pressure Test, 75°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China