

SABIC Innovative Plastics Cycloy® FXC810SK PC+ABS

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Color package may affect performance. Visual Fx PC+ABS in various metallic (sparkle) colors. High heat/good flow characteristics.

Appliance/automotive/telecommunication uses.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-FXC810SK-PCABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm @Thickness 3.20 mm	0.0040 - 0.0060 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	22 g/10 min @Load 5.00 kg, Temperature 260 °C	22 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D1238
Melt Index of Compound	22 g/10 min @Load 5.00 kg, Temperature 260 °C	22 g/10 min @Load 11.0 lb, Temperature 500 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ISO 2039-2
Hardness, H358/30	99.0 MPa	14400 psi	ISO 2039-1
Tensile Strength at Break	44.0 MPa	6380 psi	Type I, 50 mm/min; ASTM D638
	45.0 MPa	6530 psi	5 mm/min; ISO 527
	45.0 MPa	6530 psi	50 mm/min; ISO 527
Tensile Strength, Yield	51.0 MPa	7400 psi	Type I, 50 mm/min; ASTM D638
	55.0 MPa	7980 psi	5 mm/min; ISO 527
	55.0 MPa	7980 psi	50 mm/min; ISO 527
Elongation at Break	15 %	15 %	5 mm/min; ISO 527
	15 %	15 %	50 mm/min; ISO 527
	50 %	50 %	Type I, 50 mm/min; ASTM D638

Elongation at Yield Mechanical Properties	5.0 % Metric	5.0 % English	Type I, 50 mm/min; ASTM D638 Comments
	5.0 %	5.0 %	5 mm/min; ISO 527
	5.0 %	5.0 %	50 mm/min; ISO 527
Tensile Modulus	2.40 GPa	348 ksi	1 mm/min; ISO 527
	2.48 GPa	360 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	75.0 MPa	10900 psi	1.3 mm/min, 50 mm span; ASTM D790
	82.0 MPa	11900 psi	2 mm/min; ISO 178
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
	2.41 GPa	350 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	4.27 J/cm	8.00 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	24.0 kJ/m ²	11.4 ft-lb/in ²	80*10*4; ISO 180/1A
	12.0 kJ/m ²	5.71 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	2.50 J/cm ²	11.9 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	1.30 J/cm ²	6.19 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	40.0 J	29.5 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 µm/m-°C	40.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 60.0 °C	@Temperature 73.4 - 140 °F	
CTE, linear, Transverse to Flow	72.0 µm/m-°C	40.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature 23.0 -	@Temperature 73.4 -	

Thermal Properties	60.0 °C Metric	140 °F English	Comments
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	131 °C @Thickness 3.20 mm	268 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	108 °C	226 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	112 °C @Thickness 3.20 mm	234 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	128 °C	262 °F	Rate B/50; ISO 306
	130 °C	266 °F	Rate B/120; ISO 306
	143 °C	289 °F	Rate B/50; ASTM D1525

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.7 @Frequency 1.00e+6 Hz	2.7 @Frequency 1.00e+6 Hz	IEC 60250
	2.8 @Frequency 50.0 - 60.0 Hz	2.8 @Frequency 50.0 - 60.0 Hz	IEC 60250
Dielectric Strength	17.0 kV/mm @Thickness 3.20 mm	432 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
	25.0 kV/mm @Thickness 1.60 mm	635 kV/in @Thickness 0.0630 in	in oil; IEC 60243-1
	35.0 kV/mm @Thickness 0.800 mm	889 kV/in @Thickness 0.0315 in	in oil; IEC 60243-1
Dissipation Factor	0.0030 @Frequency 50.0 - 60.0 Hz	0.0030 @Frequency 50.0 - 60.0 Hz	IEC 60250
	0.0050 @Frequency 1.00e+6	0.0050 @Frequency 1.00e+6	IEC 60250

Electrical Properties	Hz Metric	Hz English	Comments
Descriptive Properties		Value	Comments
Ball Pressure Test, 125°C +/- 2°C		PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China