

SABIC Innovative Plastics Cycloy® MC1300 PC+ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Cycloy MC1300 resin is an injection moldable PC/ABS blend featuring excellent flow and impact performance. It is designed for plating applications mostly used in automotive industry.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-MC1300-PCABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	14 g/10 min	14 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 260 °C	@Load 11.0 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	44.0 MPa	6380 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	50.0 MPa	7250 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	150 %	150 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	8.6 %	8.6 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.13 GPa	309 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	72.0 MPa	10400 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	5.34 J/cm	10.0 ft-lb/in	ASTM D256
	4.27 J/cm	8.00 ft-lb/in	
	@Temperature -30.0 °C	@Temperature -22.0 °F	ASTM D256
	33.0 J	24.3 ft-lb	

Dart Drop, Total Energy Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	ASTM D3763 Comments
	40.0 J	29.5 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	40.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	90.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	50.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	115 °C	239 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	98.0 °C	208 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	111 °C	232 °F	Rate B/50; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China