

## SABIC Innovative Plastics EXTEM XH1015 TPI Resin

Category : Polymer , Thermoplastic , Polyimide, Thermoplastic

**Material Notes:**

Thermoplastic Polyimide Extem\* XH1015 Resin.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-EXTEM-XH1015-TPI-Resin.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-EXTEM-XH1015-TPI-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792
Density	1.31 g/cc	0.0473 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.60 % @Time 173000 sec	0.60 % @Time 48.0 hour	ASTM D570
Water Absorption at Saturation	2.3 %	2.3 %	ISO 62
Linear Mold Shrinkage, Flow	0.010 - 0.012 cm/cm @Thickness 3.20 mm	0.010 - 0.012 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 6.60 kg, Temperature 367 °C	10 g/10 min @Load 14.6 lb, Temperature 693 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	74.0 MPa	10700 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	101 MPa	14600 psi	5 mm/min; ISO 527
	103 MPa	14900 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	7.0 %	7.0 %	5 mm/min; ISO 527
	10 %	10 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	5 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	3.10 GPa	450 ksi	1 mm/min; ISO 527
	3.42 GPa	496 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	120 MPa	17400 psi	2 mm/min; ISO 178

Mechanical Properties	168 MPa Metric	24400 psi English	1.3 mm/min, 50 mm span; ASTM D790 Comments
Flexural Modulus	2.87 GPa	416 ksi	2 mm/min; ISO 178
	3.13 GPa	454 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.430 J/cm	0.806 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	4.00 kJ/m <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 μm/m-°C	27.8 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 150 °C	@Temperature 73.4 - 302 °F	
CTE, linear, Transverse to Flow	51.0 μm/m-°C	28.3 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 150 °C	@Temperature 73.4 - 302 °F	
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	223 °C	433 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	235 °C	455 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
	237 °C	459 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	247 °C	477 °F	Rate B/120; ISO 306
	250 °C	482 °F	Rate B/50; ISO 306
	260 °C	500 °F	Rate B/50; ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China