

SABIC Innovative Plastics LNP LUBRICOMP DBL349E PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Lubricomp* DBL349E is a compound based on Polycarbonate resin containing Glass Bead, PTFE, Flame Retardant. Added features of this material include: LNP* Lubricomp* DBL349E is a compound based on Polycarbonate resin containing Glass Bead, PTFE, Flame Retardant. Added features of this material include: Internally Lubricated, Flame Retardant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-DBL349E-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ASTM D792
	1.48 g/cc	0.0535 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0054 cm/cm	0.0054 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0069 cm/cm	0.0069 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	37.0 MPa	5370 psi	ASTM D638
	38.0 MPa	5510 psi	ISO 527
Tensile Strength, Yield	41.0 MPa	5950 psi	ASTM D638
	41.0 MPa	5950 psi	ISO 527
Elongation at Break	7.6 %	7.6 %	ISO 527
	9.0 %	9.0 %	ASTM D638
Elongation at Yield	2.9 %	2.9 %	ASTM D638
	2.9 %	2.9 %	ISO 527
Tensile Modulus	2.97 GPa	431 ksi	1 mm/min; ISO 527
	3.44 GPa	499 ksi	50 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
Flexural Strength	78.0 MPa	11300 psi	ISO 178
Flexural Modulus	2.75 GPa	399 ksi	ASTM D790
	2.90 GPa	421 ksi	ISO 178
Izod Impact, Notched	0.580 J/cm	1.09 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.64 J/cm	8.69 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	15.0 J	11.1 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	4.00 J	2.95 ft-lb	Multiaxial Impact; ISO 6603
Coefficient of Friction, Dynamic	0.52	0.52	ASTM D3702 Modified
Coefficient of Friction, Static	0.70	0.70	ASTM D3702 Modified
K (wear) Factor	181 x 10 ⁻⁸ mm ³ /N-M	90.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	Washer; ASTM D3702 Modified

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	64.8 µm/m-°C	36.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	65.0 µm/m-°C	36.1 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	64.0 µm/m-°C	35.6 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	64.8 µm/m-°C	36.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	141 °C	286 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	129 °C	264 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Thermal Properties	128 °C Metric	262 °F English	Comments
	@Thickness 3.20 mm	@Thickness 0.126 in	PP (HDPE), ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China