

**SABIC Innovative Plastics LNP LUBRICOMP DFL32XXC PC**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

LNP LUBRICOMP\* DFL32XXC is a compound based on Polycarbonate resin containing 10% Glass Fiber, 15% PTFE. Added features of this material include: Internally Lubricated.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-LUBRICOMP-DFL32XXC-PC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-DFL32XXC-PC.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ASTM D792
Moisture Absorption	0.110 %	0.110 %	50% RH, 24 hrs; ASTM D570
	0.170 %	0.170 %	23°C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0023 cm/cm	0.0023 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0067 cm/cm	0.0067 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0070 cm/cm	0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	71.0 MPa	10300 psi	ISO 527
	73.0 MPa	10600 psi	ASTM D638
Elongation at Break	2.8 %	2.8 %	ISO 527
	3.1 %	3.1 %	ASTM D638
Tensile Modulus	4.28 GPa	621 ksi	1 mm/min; ISO 527
	4.35 GPa	631 ksi	50 mm/min; ASTM D638
Flexural Strength	114 MPa	16500 psi	ISO 178
	123 MPa	17800 psi	ASTM D790
Flexural Modulus	4.17 GPa	605 ksi	ISO 178

Mechanical Properties	4.35 GPa Metric	631 ksi English	ASTM D790 Comments
Izod Impact, Notched	0.900 J/cm	1.69 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.34 J/cm	10.0 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	34.0 kJ/m <sup>2</sup>	16.2 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U
Dart Drop, Total Energy	11.0 J	8.11 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	4.00 J	2.95 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	141 °C @Thickness 3.20 mm	286 °F @Thickness 0.126 in	unannealed; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China