

## SABIC Innovative Plastics LNP LUBRICOMP Lexan\_WR5210R PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

LNP\* Lubricomp\* Lexan\_WR5210R compound is a wear resistant, 7% PTFE filled material.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-LUBRICOMP-LexanWR5210R-PC-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-LexanWR5210R-PC-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	21.5 g/10 min	21.5 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 Â°C	@Load 2.65 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	53.0 MPa	7690 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	75 %	75 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	83.0 MPa	12000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.03 GPa	294 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.81 J/cm	3.39 ft-lb/in	ASTM D256
Dart Drop, Total Energy	38.0 J	28.0 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	126 Â°C	259 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
UL RTI, Electrical	80.0 Â°C	176 Â°F	UL 746B
UL RTI, Mechanical with Impact	80.0 Â°C	176 Â°F	UL 746B
UL RTI, Mechanical without Impact	80.0 Â°C	176 Â°F	UL 746B
Flammability, UL94	HB	HB	UL 94
	@Thickness 1.49 mm	@Thickness 0.0587 in	

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Gloss	52 %	52 %	untextured, 60 degrees; ASTM D523

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China