

SABIC Innovative Plastics LNP LUBRICOMP RAL22S PA 66 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LNP* Lubricomp* RAL22S is a compound based on Nylon 66 resin containing PTFE, Aramid Fiber. Added features of this material include:
Internally Lubricated.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-RAL22S-PA-66-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
	1.22 g/cc	0.0441 lb/in ³	ISO 1183
Moisture Absorption	0.700 %	0.700 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.019 cm/cm	0.019 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0192 cm/cm	0.0192 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0195 cm/cm	0.0195 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.020 cm/cm	0.020 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	79.0 MPa	11500 psi	ISO 527
	81.0 MPa	11700 psi	ASTM D638
Elongation at Break	8.1 %	8.1 %	ASTM D638
	9.5 %	9.5 %	ISO 527
Tensile Modulus	3.44 GPa	499 ksi	50 mm/min; ASTM D638
	3.50 GPa	508 ksi	1 mm/min; ISO 527
Flexural Strength	110 MPa	16000 psi	ASTM D790
	117 MPa	17000 psi	ISO 178
Flexural Modulus	2.96 GPa	429 ksi	ASTM D790

Mechanical Properties	3.50 GPa Metric	508 ksi English	ISO 178 Comments
Izod Impact, Notched	1.33 J/cm	2.49 ft-lb/in	ASTM D256
Izod Impact, Unnotched	7.47 J/cm	14.0 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	48.0 kJ/m ²	22.8 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	6.00 J	4.43 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	1.00 J	0.738 ft-lb	Multiaxial Impact; ISO 6603
Coefficient of Friction, Dynamic	0.55	0.55	ASTM D3702 Modified
Coefficient of Friction, Static	0.46	0.46	ASTM D3702 Modified
K (wear) Factor	26.2 x 10 ⁻⁸ mm ³ /N-M	13.0 x 10 ⁻¹⁰ in ³ - min/ft-lb-hr	Washer; ASTM D3702 Modified

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	73.6 Åµm/m-Å°C	40.9 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	73.8 Åµm/m-Å°C	41.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	82.6 Åµm/m-Å°C	45.9 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	82.8 Åµm/m-Å°C	46.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	248 Å°C	478 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	193 Å°C	379 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	198 Å°C	388 Å°F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China