

SABIC Innovative Plastics LNP LUBRICOMP UFL269SA PPA (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

Material Notes:

LNP* Lubricomp* UFL269SA is a compound based on Polyphthalamide resin containing Glass Fiber, PTFE, Flame Retardant. Added features of this material include: Internally Lubricated, Heat Stabilized, Flame Retardant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-UFL269SA-PPA-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.71 g/cc	0.0618 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	162 MPa	23500 psi	ASTM D638
Elongation at Break	1.7 %	1.7 %	ASTM D638
Tensile Modulus	13.65 GPa	1980 ksi	50 mm/min; ASTM D638
Flexural Strength	227 MPa	32900 psi	ASTM D790
Flexural Modulus	12.82 GPa	1859 ksi	ASTM D790
Izod Impact, Notched	0.850 J/cm	1.59 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.61 J/cm	8.64 ft-lb/in	ASTM D4812
Coefficient of Friction, Dynamic	0.47	0.47	ASTM D3702 Modified
Coefficient of Friction, Static	0.38	0.38	ASTM D3702 Modified
K (wear) Factor	171 x 10 ⁻⁸ mm ³ /N-M	85.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	Washer; ASTM D3702 Modified

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	273 Â°C	523 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Flammability, UL94	V-0	V-0	UL 94 by SABIC-IP

Thermal Properties	@Thickness 1.50 mm Metric	@Thickness 0.0591 in English	Comments
--------------------	------------------------------	---------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China