

## SABIC Innovative Plastics LNP LUBRICOMP WFI18 PBT (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

LNP\* Lubricomp\* WFI18 is a compound based on Polybutylene Terephthalate resin containing Glass Fiber, Silicone.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-LUBRICOMP-WFI18-PBT-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-WFI18-PBT-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.59 g/cc	0.0574 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	118 MPa	17100 psi	5 mm/min; ISO 527
Elongation at Break	2.1 %	2.1 %	5 mm/min; ISO 527
Tensile Modulus	11.1 GPa	1610 ksi	1 mm/min; ISO 527
Flexural Yield Strength	156 MPa	22600 psi	2 mm/min; ISO 178
Flexural Modulus	7.90 GPa	1150 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	45.0 kJ/m <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	11.1 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
CTE, linear, Transverse to Flow	137 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	76.1 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	218 $\text{Å}^\circ\text{C}$	424 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	188 $\text{Å}^\circ\text{C}$	370 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China