

SABIC Innovative Plastics LNP STAT-KON DFD029 PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Stat-kon* DFD029 is a compound based on Polycarbonate resin containing Glass Fiber, Flame Retardant, Carbon Powder. Added features of this material include: Electrically Conductive, Flame Retardant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-DFD029-PC-Europe-Africa-Middle-East.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	75.0 MPa	10900 psi	5 mm/min; ISO 527
Elongation at Break	2.7 %	2.7 %	5 mm/min; ISO 527
Tensile Modulus	4.10 GPa	595 ksi	1 mm/min; ISO 527
Flexural Strength	105 MPa	15200 psi	2 mm/min; ISO 178
Flexural Modulus	3.70 GPa	537 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	45.0 Åµm/m-Å°C	25.0 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
CTE, linear, Transverse to Flow	68.0 Åµm/m-Å°C	37.8 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	147 Å°C	297 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	141 Å°C	286 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+6 - 1.00e+9 ohm	1.00e+6 - 1.00e+9 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China