

SABIC Innovative Plastics LNP STAT-KON DX09315C PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Stat-Kon* DX09315C is carbon fiber filled polycarbonate composite with good flow ability, and high level of cleanliness for the most demanding application. A unique feature of this material is its low C18-C40 hydrocarbons. This compound is manufactured using LNP CCS Technology.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-DX09315C-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm @Thickness 3.20 mm	0.0010 - 0.0020 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0030 - 0.0040 cm/cm @Thickness 3.20 mm	0.0030 - 0.0040 in/in @Thickness 0.126 in	SABIC Method
Melt Index of Compound	26 g/10 min @Load 2.16 kg, Temperature 300 Â°C	26 g/10 min @Load 4.76 lb, Temperature 572 Â°F	MVR [cm^3/10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	123 MPa	17800 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	9.81 GPa	1420 ksi	5 mm/min; ASTM D638
Flexural Strength	201 MPa	29200 psi	ASTM D790
Flexural Modulus	8.13 GPa	1180 ksi	ASTM D790
Izod Impact, Notched	0.940 J/cm	1.76 ft-lb/in	ASTM D256
Izod Impact, Unnotched	7.32 J/cm	13.7 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	13.0 Âµm/m-Â°C @Temperature -40.0 - 40.0 Â°C	7.22 Âµin/in-Â°F @Temperature -40.0 - 104 Â°F	ASTM E 831
CTE, linear, Transverse to Flow	70.0 Âµm/m-Â°C @Temperature -40.0 -	38.9 Âµin/in-Â°F @Temperature -40.0 -	ASTM E 831

Thermal Properties	40.0 Å°C Metric	104 Å°F English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	125 Å°C @Thickness 3.20 mm	257 Å°F @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	10000 - 500000 ohm	10000 - 500000 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China