

SABIC Innovative Plastics LNP STAT-KON DX12411C PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* STAT-KON* DX12411C is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added features of this material include: Electrically Conductive, Clean Compounding System.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-DX12411C-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Density	1.246 g/cc	0.04501 lb/in ³	ASTM D792
Moisture Absorption	0.150 %	0.150 %	50% RH, 24 hrs; ASTM D570
	0.220 %	0.220 %	23 ^o C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0085 cm/cm	0.0085 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	47.0 MPa	6820 psi	Type I, 5 mm/min; ASTM D638
	47.0 MPa	6820 psi	5 mm/min; ISO 527
Tensile Strength, Yield	54.0 MPa	7830 psi	5 mm/min; ISO 527
	55.0 MPa	7980 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	12.3 %	12.3 %	5 mm/min; ISO 527
	19 %	19 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	4.6 %	4.6 %	5 mm/min; ISO 527
	4.7 %	4.7 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	2.56 GPa	371 ksi	1 mm/min; ISO 527
	2.63 GPa	381 ksi	5 mm/min; ASTM D638
Flexural Strength	88.0 MPa	12800 psi	ISO 178
Flexural Modulus	2.54 GPa	368 ksi	2 mm/min; ISO 178

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	2.96 J/cm	5.55 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	18.0 kJ/m ²	8.57 ft-lb/in ²	80*10*4; ISO 180/1A
Dart Drop, Total Energy	34.0 J @Temperature 23.0 Â°C	25.1 ft-lb @Temperature 73.4 Â°F	ASTM D3763
Impact Test	33.0 J	24.3 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	71.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	39.4 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
CTE, linear, Transverse to Flow	72.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	40.0 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	138 Â°C	280 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	139 Â°C @Thickness 3.20 mm	282 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	107 Â°C	225 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	92.0 Â°C @Thickness 3.20 mm	198 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1000 - 1.00e+6 ohm- cm	1000 - 1.00e+6 ohm- cm	ASTM D257
Surface Resistance	1000 - 1.00e+6 ohm	1000 - 1.00e+6 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China