

SABIC Innovative Plastics LNP STAT-KON EE005E PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

LNP STAT-KON* EE005E is a compound based on Polyetherimide resin containing Carbon Fiber. Added features of this material include:
Easy Molding.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-EE005E-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
	1.365 g/cc	0.04931 lb/in ³	ASTM D792
Moisture Absorption	0.160 %	0.160 %	50% RH, 24 hrs; ASTM D570
	0.230 %	0.230 %	23 ^o C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.00050 - 0.0030 cm/cm	0.00050 - 0.0030 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	194 MPa	28100 psi	ISO 527
	200 MPa	29000 psi	ASTM D638
Elongation at Break	2.1 %	2.1 %	ASTM D638
	2.1 %	2.1 %	ISO 527
Tensile Modulus	11.7 GPa	1700 ksi	1 mm/min; ISO 527
	12.33 GPa	1788 ksi	50 mm/min; ASTM D638
Flexural Strength	276 MPa	40000 psi	ISO 178
	277 MPa	40200 psi	ASTM D790

Mechanical Properties	Metric	English	Comments
	15.01 GPa	2177 ksi	ISO 178
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.48 J/cm	8.39 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	29.0 kJ/m ²	13.8 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	10.0 J	7.38 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	7.00 J	5.16 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.0 Åµm/m-Å°C	10.6 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	19.2 Åµm/m-Å°C	10.7 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	27.1 Åµm/m-Å°C	15.1 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	27.1 Åµm/m-Å°C	15.1 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	207 Å°C	405 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	207 Å°C	405 Å°F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	100 - 1.00e+6 ohm-cm	100 - 1.00e+6 ohm-cm	ASTM D257
Surface Resistance	100 ohm - 1e+05	100 ohm - 1e+05	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China