

## SABIC Innovative Plastics LNP STAT-KON OCL13XXP PPS - LINEAR (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

### Material Notes:

LNP\* Stat-kon\* OCL13XXP is a compound based on PPS - LINEAR resin containing PTFE, Carbon Fiber. Added features of this material include: Electrically Conductive.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-STAT-KON-OCL13XXP-PPS-LINEAR-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-OCL13XXP-PPS-LINEAR-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.00050 - 0.0025 cm/cm	0.00050 - 0.0025 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	157 MPa	22800 psi	5 mm/min; ISO 527
Elongation at Break	1.5 %	1.5 %	5 mm/min; ISO 527
Tensile Modulus	12.6 GPa	1830 ksi	1 mm/min; ISO 527
Flexural Strength	212 MPa	30700 psi	2 mm/min; ISO 178
Flexural Modulus	11.1 GPa	1610 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	25.0 kJ/m <sup>2</sup>	11.9 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	14.0 Åµm/m-Å°C	7.78 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
CTE, linear, Transverse to Flow	52.0 Åµm/m-Å°C	28.9 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	243 Å°C	469 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Electrical Properties	Metric	English	Comments
Surface Resistance	100 - 10000 ohm	100 - 10000 ohm	ASTM D257

Electrical Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China