

SABIC Innovative Plastics LNP STAT-KON OE004A PPS - BRANCHED (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

LNP* STATKON* OE004A is a compound based on PPS (branched) resin containing Carbon Fiber. Added features include: Electrically Conductive.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-OE004A-PPS-BRANCHED-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Water Absorption	0.040 % @Time 86400 sec	0.040 % @Time 24.0 hour	ISO 62-1
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	185 MPa	26800 psi	5 mm/min; ISO 527
Elongation at Break	1.1 %	1.1 %	5 mm/min; ISO 527
Tensile Modulus	21.63 GPa	3137 ksi	1 mm/min; ISO 527
Flexural Yield Strength	242 MPa	35100 psi	2 mm/min; ISO 178
Flexural Modulus	15.7 GPa	2280 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	11.0 μm/m-°C @Temperature 23.0 - 60.0 °C	6.11 μin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2
CTE, linear, Transverse to Flow	50.0 μm/m-°C @Temperature 23.0 - 60.0 °C	27.8 μin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	277 °C	531 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa	256 °C	493 °F	Flatw 80*10*4 sp=64mm; ISO 75/ Af

<small>(264 psi)</small> Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	UL 94

Electrical Properties	Metric	English	Comments
Surface Resistance	1000 - 1.00e+6 ohm	1000 - 1.00e+6 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China