

SABIC Innovative Plastics LNP STAT-KON OEP32 PPS - Linear

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

LNP STAT-KON* OEP32 is a compound based on PPS - Linear resin containing 10% Carbon Fiber, 15% PTFE/Silicone. Added features of this material include: Electrically Conductive, Wear Resistant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-OEP32-PPS-Linear.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ASTM D792
	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	125 MPa	18100 psi	ISO 527
	127 MPa	18400 psi	ASTM D638
Elongation at Break	1.6 %	1.6 %	ASTM D638
	2.0 %	2.0 %	ISO 527
Tensile Modulus	10.56 GPa	1532 ksi	50 mm/min; ASTM D638
	10.59 GPa	1536 ksi	1 mm/min; ISO 527
Flexural Strength	193 MPa	28000 psi	ASTM D790
	431 MPa	62500 psi	ISO 178
Flexural Modulus	8.54 GPa	1240 ksi	ASTM D790
Izod Impact, Notched	0.370 J/cm	0.693 ft-lb/in	ASTM D256

Izod Impact, Unnotched Mechanical Properties	4.28 J/cm Metric	8.02 ft-lb/in English	ASTM D4812 Comments
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	23.0 kJ/m ²	10.9 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	8.00 J	5.90 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	2.00 J	1.48 ft-lb	Multiaxial Impact; ISO 6603
Coefficient of Friction, Dynamic	0.32	0.32	ASTM D3702 Modified
Coefficient of Friction, Static	0.33	0.33	ASTM D3702 Modified
K (wear) Factor	78.6 x 10 ⁻⁸ mm ³ /N-M	39.0 x 10 ⁻¹⁰ in ³ - min/ft-lb-hr	Washer; ASTM D3702 Modified

Electrical Properties	Metric	English	Comments
Surface Resistance	100 - 10000 ohm	100 - 10000 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China