

SABIC Innovative Plastics LNP STAT-KON QD000I PA 6/10 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 610

Material Notes:

LNP STAT-KON* QD000I is a compound based on Nylon 6/10 resin containing Carbon Powder. Added features of this material include:
Electrically Conductive.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-QD000I-PA-610-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	ASTM D792
Moisture Absorption	0.280 %	0.280 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm @Time 86400 sec	0.0010 - 0.0030 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.0020 - 0.0040 cm/cm @Time 86400 sec	0.0020 - 0.0040 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	31.0 MPa	4500 psi	ASTM D638
Elongation at Break	52.7 %	52.7 %	ASTM D638
Flexural Strength	54.0 MPa	7830 psi	ASTM D790
Flexural Modulus	1.72 GPa	249 ksi	ASTM D790
Izod Impact, Notched	6.03 J/cm	11.3 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	117 µm/m-°C @Temperature -40.0 - 40.0 °C	65.0 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
CTE, linear, Transverse to Flow	117 µm/m-°C @Temperature -40.0 - 40.0 °C	65.0 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C @Thickness 3.20 mm	131 °F @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	100 - 10000 ohm-cm Metric	100 - 10000 ohm-cm English	ASTM D257 Comments
Surface Resistance	100 - 10000 ohm	100 - 10000 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China