

SABIC Innovative Plastics LNP STAT-KON ZE004 MODIFIED POLYPHENYLENE (Asia Pacific)

Category : Polymer , Thermoplastic

Material Notes:

LNP* Stat-kon* ZE004 is a compound based on MODIFIED POYPHENYLENE resin containing Carbon Fiber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-ZE004-MODIFIED-POLYPHENYLENE-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792
	1.17 g/cc	0.0423 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0030 cm/cm	0.0030 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0053 cm/cm	0.0053 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	103 MPa	14900 psi	ISO 527
	104 MPa	15100 psi	ASTM D638
Tensile Strength, Yield	54.0 MPa	7830 psi	ISO 527
	80.0 MPa	11600 psi	ASTM D638
Elongation at Break	0.50 %	0.50 %	ASTM D638
	0.90 %	0.90 %	ISO 527
Tensile Modulus	14.72 GPa	2135 ksi	1 mm/min; ISO 527
	24.82 GPa	3600 ksi	50 mm/min; ASTM D638
Flexural Strength	151 MPa	21900 psi	ISO 178
	179 MPa	26000 psi	ASTM D790

Flexural Modulus Mechanical Properties	12.7 GPa Metric	1840 ksi English	ISO 178 Comments
	24.13 GPa	3500 ksi	ASTM D790
Izod Impact, Notched	0.370 J/cm	0.693 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.99 J/cm	5.60 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	4.00 kJ/m ²	1.90 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	17.0 kJ/m ²	8.09 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	48.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	26.7 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	48.6 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	27.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	36.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	20.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	37.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	20.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	141 $\text{Å}^\circ\text{C}$	286 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	139 $\text{Å}^\circ\text{C}$	282 $\text{Å}^\circ\text{F}$	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	135 $\text{Å}^\circ\text{C}$	275 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	137 $\text{Å}^\circ\text{C}$	279 $\text{Å}^\circ\text{F}$	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	100 - 1.00e+6 ohm	100 - 1.00e+6 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China