

## SABIC Innovative Plastics LNP STAT-LOY A30009 ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer

### Material Notes:

LNP\* Stat-loy\* A30009 is a compound based on Acrylonitrile Butadiene Styrene resin containing Flame Retardant. Added features of this material include: Antistat, Flame Retardant.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-STAT-LOY-A30009-ABS-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-LOY-A30009-ABS-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ASTM D792
	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	2.30 %	2.30 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0079 cm/cm	0.0079 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0088 cm/cm	0.0088 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.0 MPa	3480 psi	ASTM D638
	28.0 MPa	4060 psi	ISO 527
Tensile Strength, Yield	32.0 MPa	4640 psi	ASTM D638
	32.0 MPa	4640 psi	ISO 527
Elongation at Break	15.2 %	15.2 %	ISO 527
	35.8 %	35.8 %	ASTM D638
Elongation at Yield	3.5 %	3.5 %	ISO 527
	3.8 %	3.8 %	ASTM D638
Tensile Modulus	1.72 GPa	249 ksi	1 mm/min; ISO 527

Mechanical Properties	2.06 GPa Metric	299 ksi English	50 mm/min; ASTM D638 Comments
Flexural Strength	41.0 MPa	5950 psi	ASTM D790
	47.0 MPa	6820 psi	ISO 178
Flexural Modulus	2.00 GPa	290 ksi	ISO 178
	2.06 GPa	299 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.49 ft-lb/in	ASTM D256
Izod Impact, Unnotched	16.98 J/cm	31.81 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	11.0 kJ/m <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	141 kJ/m <sup>2</sup>	67.1 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U
Dart Drop, Total Energy	14.0 J	10.3 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	4.00 J	2.95 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	114 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	63.3 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	115 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	63.9 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	95.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	52.8 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	95.4 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	53.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	94.0 $\text{Å}^\circ\text{C}$	201 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	95.0 $\text{Å}^\circ\text{C}$	203 $\text{Å}^\circ\text{F}$	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	81.0 $\text{Å}^\circ\text{C}$	178 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	81.0 $\text{Å}^\circ\text{C}$	178 $\text{Å}^\circ\text{F}$	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+9 - 1.00e+11 ohm	1.00e+9 - 1.00e+11 ohm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China