

## SABIC Innovative Plastics LNP STAT-LOY SLWM2105 PBT+PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

Anti-static PBT/PC blend, mineral 5% filled product

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-STAT-LOY-SLWM2105-PBTPC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-LOY-SLWM2105-PBTPC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.015 - 0.018 cm/cm @Thickness 3.20 mm	0.015 - 0.018 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	30 g/10 min @Load 1.20 kg, Temperature 250 Â°C	30 g/10 min @Load 2.65 lb, Temperature 482 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	46.0 MPa	6670 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	46.0 MPa	6670 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	20 %	20 %	Type I, 10 mm/min; SABIC - Japan Method
Elongation at Yield	20 %	20 %	Type I, 10 mm/min; SABIC - Japan Method
Tensile Modulus	2.42 GPa	351 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	77.0 MPa	11200 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.410 J/cm	0.768 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	161 Â°C @Thickness 3.20 mm	322 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	9.00e+12 ohm	9.00e+12 ohm	ASTM D257

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**