

SABIC Innovative Plastics LNP THERMOCOMP DB008ERP PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Thermocomp* DB008ERP is a compound based on Polycarbonate resin containing Glass Bead. Added features of this material include: Easy Molding, Mold Release.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-DB008ERP-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0067 cm/cm	0.0067 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0070 cm/cm	0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm	0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0073 cm/cm	0.0073 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	42.0 MPa	6090 psi	ASTM D638
Elongation at Break	3.2 %	3.2 %	ASTM D638
Tensile Modulus	3.96 GPa	574 ksi	50 mm/min; ASTM D638
Flexural Strength	75.0 MPa	10900 psi	ASTM D790
Flexural Modulus	3.84 GPa	557 ksi	ASTM D790
Izod Impact, Notched	0.420 J/cm	0.787 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.00 J/cm	7.49 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	132 Å°C	270 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China