

SABIC Innovative Plastics LNP THERMOCOMP JF004RXP PES (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

LNP* Thermocomp* JF004RXP is a compound based on Polyethersulfone resin containing Glass Fiber. Added features of this material include: Mold Release.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-JF004RXP-PES-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0025 - 0.0045 cm/cm	0.0025 - 0.0045 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	122 MPa	17700 psi	5 mm/min; ISO 527
Elongation at Break	2.4 %	2.4 %	5 mm/min; ISO 527
Tensile Modulus	7.10 GPa	1030 ksi	1 mm/min; ISO 527
Flexural Modulus	6.00 GPa	870 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	35.0 kJ/m ²	16.7 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	223 Â°C	433 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	219 Â°C	426 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
Flammability, UL94	V-0	V-0	UL 94 by SABIC-IP
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	V-0	V-0	UL 94
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China