

SABIC Innovative Plastics LNP THERMOCOMP JF004Z PES (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

LNP* Thermocomp* JF004Z is a compound based on Polyethersulfone resin containing Glass Fiber. Added features of this material include:
HV.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-JF004Z-PES-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.51 g/cc	0.0546 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0025 - 0.0045 cm/cm	0.0025 - 0.0045 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	5 mm/min; ISO 527
Elongation at Break	2.7 %	2.7 %	5 mm/min; ISO 527
Tensile Modulus	6.70 GPa	972 ksi	1 mm/min; ISO 527
Flexural Yield Strength	178 MPa	25800 psi	2 mm/min; ISO 178
Flexural Modulus	5.80 GPa	841 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	40.0 kJ/m ²	19.0 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	225 °C	437 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	221 °C	430 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China