

SABIC Innovative Plastics LNP THERMOCOMP LC008EXP PEEK (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

Material Notes:

LNP* THERMOCOMP* LC008EXP is a compound based on Polyetheretherketone containing Carbon Fiber. Added features include Electrically Conductive, Easy Molding.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-LC008EXP-PEEK-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	256 MPa	37100 psi	5 mm/min; ISO 527
Elongation at Break	1.6 %	1.6 %	5 mm/min; ISO 527
Tensile Modulus	26.2 GPa	3800 ksi	1 mm/min; ISO 527
Flexural Strength	341 MPa	49500 psi	2 mm/min; ISO 178
Flexural Modulus	22.9 GPa	3320 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	45.0 kJ/m ²	21.4 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	4.00 Åµm/m-Å°C	2.22 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
CTE, linear, Transverse to Flow	41.0 Åµm/m-Å°C	22.8 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	>= 300 Å°C	>= 572 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China