

SABIC Innovative Plastics LNP THERMOCOMP LF005 PEEK (Asia Pacific)

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

Material Notes:

LNP* Thermocomp* LF005 is a compound based on Polyetheretherketone resin containing Glass Fiber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-LF005-PEEK-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ASTM D792
	1.48 g/cc	0.0535 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0064 cm/cm	0.0064 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.011 cm/cm	0.011 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	156 MPa	22600 psi	ASTM D638
	158 MPa	22900 psi	ISO 527
Tensile Strength, Yield	156 MPa	22600 psi	ASTM D638
	158 MPa	22900 psi	ISO 527
Elongation at Break	2.7 %	2.7 %	ASTM D638
	2.7 %	2.7 %	ISO 527
Elongation at Yield	2.6 %	2.6 %	ISO 527
	2.7 %	2.7 %	ASTM D638
Tensile Modulus	11.4 GPa	1650 ksi	1 mm/min; ISO 527
	11.72 GPa	1700 ksi	50 mm/min; ASTM D638
Flexural Strength	243 MPa	35200 psi	ISO 178

Mechanical Properties	Metric	English	Comments
Flexural Modulus	8.60 GPa	1250 ksi	ISO 178
	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	0.900 J/cm	1.69 ft-lb/in	ASTM D256
Izod Impact, Unnotched	9.34 J/cm	17.5 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	60.0 kJ/m ²	28.6 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	14.0 J	10.3 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	3.00 J	2.21 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	5.40 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	3.00 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	51.7 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	28.7 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	1.80 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	1.00 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	19.4 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	10.8 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	239 $\text{Å}^\circ\text{C}$	462 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China