

SABIC Innovative Plastics LNP THERMOCOMP Lexan_SP7604 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-LexanSP7604-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
Water Absorption	0.12 % @Time 86400 sec	0.12 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0030 cm/cm @Thickness 3.20 mm	0.0020 - 0.0030 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	96.0 MPa	13900 psi	SABIC - Japan Method
Elongation at Break	4.0 - 6.0 %	4.0 - 6.0 %	SABIC - Japan Method
Flexural Strength	132 MPa	19100 psi	ASTM D790
Flexural Modulus	5.49 GPa	796 ksi	ASTM D790
Izod Impact, Notched	0.780 J/cm	1.46 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 - 55.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	16.7 - 30.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	TMA
Deflection Temperature at 0.46 MPa (66 psi)	100 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	212 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648
Flammability, UL94	V-0 @Thickness 0.750 mm	V-0 @Thickness 0.0295 in	UL 94

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China