

SABIC Innovative Plastics LNP THERMOCOMP MF004S PP

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

LNP THERMOCOMP* MF004S is a compound based on Polypropylene resin containing 20% Glass Fiber. Added features of this material include: Chemically Coupled, Heat Stabilized.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-MF004S-PP.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Time 86400 sec	0.0040 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.010 cm/cm @Time 86400 sec	0.010 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	66.0 MPa	9570 psi	ASTM D638
Elongation at Break	3.1 %	3.1 %	ASTM D638
Flexural Strength	106 MPa	15400 psi	ASTM D790
Flexural Modulus	4.13 GPa	599 ksi	ASTM D790
Izod Impact, Notched	0.420 J/cm	0.787 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.34 J/cm	10.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	145 Â°C @Thickness 3.20 mm	293 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China