

**SABIC Innovative Plastics LNP THERMOCOMP MX99432 PP (Asia Pacific)**

Category : Polymer , Thermoplastic , Polypropylene (PP)

**Material Notes:**

LNP\* Thermocomp\* MX99432 is a compound based on Polypropylene resin containing Glass Fiber.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-MX99432-PP-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-MX99432-PP-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	57.0 MPa	8270 psi	ASTM D638
Elongation at Break	2.9 %	2.9 %	ASTM D638
Tensile Modulus	5.27 GPa	764 ksi	50 mm/min; ASTM D638
Flexural Strength	89.0 MPa	12900 psi	ASTM D790
Flexural Modulus	4.61 GPa	669 ksi	ASTM D790
Izod Impact, Notched	0.740 J/cm	1.39 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.09 J/cm	9.54 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	145 Å°C	293 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China