

SABIC Innovative Plastics LNP THERMOCOMP NX11302 PC+ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

This is a PC/ABS compound with colorable, good plating, surface and mechanical performance, a good candidate for Laser Direct Structuring applications

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-NX11302-PCABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Water Absorption	0.010 % @Time 86400 sec	0.010 % @Time 24.0 hour	ASTM D570
Moisture Absorption	0.0100 %	0.0100 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Time 86400 sec	0.0060 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 cm/cm @Time 86400 sec	0.0060 in/in @Time 24.0 hour	ASTM D955
Melt Index of Compound	14 g/10 min @Load 5.00 kg, Temperature 260 °C	14 g/10 min @Load 11.0 lb, Temperature 500 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	46.0 MPa	6670 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	47.0 MPa	6820 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	75 %	75 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	4.6 %	4.6 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.35 GPa	341 ksi	50 mm/min; ASTM D638
Flexural Strength	78.0 MPa	11300 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Yield Strength	79.0 MPa	11500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.23 GPa	323 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	5.50 J/cm	10.3 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	71.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	39.4 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	76.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	42.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	106 $\text{Å}^\circ\text{C}$	223 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.94	2.94	IEC 60250
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	
Dissipation Factor	0.0057	0.0057	IEC 60250
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China