

## SABIC Innovative Plastics LNP THERMOCOMP PB006EQ PA 6 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 6

**Material Notes:**

LNP \*THERMOCOMP\* PB006EQ is a compound based on PA 6 containing Glass Bead. Added features include Reduced Moisture.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-PB006EQ-PA-6-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-PB006EQ-PA-6-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.018 cm/cm	0.018 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	42.0 MPa	6090 psi	5 mm/min; ISO 527
Elongation at Break	10 %	10 %	5 mm/min; ISO 527
Flexural Yield Strength	56.0 MPa	8120 psi	2 mm/min; ISO 178
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	4.00 kJ/m <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	40.0 kJ/m <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	109 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	60.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	@Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	116 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	64.4 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	@Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	61.0 $\text{Å}^\circ\text{C}$	142 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China