

## SABIC Innovative Plastics LNP THERMOCOMP PF00CS PA 6 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 6

### Material Notes:

LNP\* THERMOCOMP\* PF00CS is a compound based on PA6 resin containing Glass Fiber.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-PF00CS-PA-6-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-PF00CS-PA-6-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.72 g/cc	0.0621 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	206 MPa	29900 psi	5 mm/min; ISO 527
Elongation at Break	3.0 %	3.0 %	5 mm/min; ISO 527
	3.7 %	3.7 %	Flexural Strain, break, 2 mm/min; ISO 178
Tensile Modulus	20.4 GPa	2960 ksi	1 mm/min; ISO 527
Flexural Strength	307 MPa	44500 psi	2 mm/min; ISO 178
Flexural Yield Strength	312 MPa	45300 psi	2 mm/min; ISO 178
Flexural Modulus	16.7 GPa	2420 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	13.0 kJ/m <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	90.0 kJ/m <sup>2</sup>	42.8 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	17.0 Åµm/m-Å°C	9.44 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
CTE, linear, Transverse to Flow	65.0 Åµm/m-Å°C	36.1 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	219 Å°C	426 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	206 Å°C	403 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Thermal Properties	Metric	English	Comments
Flammability, UL 94	@Thickness 1.50 mm	@Thickness 0.0591 in	UL 94

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China