

**SABIC Innovative Plastics LNP THERMOCOMP PX92248 PA 6**

Category : Polymer , Thermoplastic , Nylon , Nylon 6

**Material Notes:**

LNP\* THERMOCOMP\* PX92248 is a compound based on Nylon 6 resin containing Proprietary Filler(s).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-PX92248-PA-6.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-PX92248-PA-6.php)

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	107 MPa	15500 psi	ASTM D638
	107 MPa	15500 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
	2.5 %	2.5 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	8.84 GPa	1280 ksi	50 mm/min; ASTM D638
Flexural Strength	179 MPa	26000 psi	ASTM D790
	179 MPa	26000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	7.22 GPa	1050 ksi	ASTM D790
	7.22 GPa	1050 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.38 J/cm	2.59 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.43 J/cm	15.8 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	195 Â°C	383 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China