

SABIC Innovative Plastics LNP THERMOCOMP SF00A PA12 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Glass filled Nylon 12

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-SF00A-PA12-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ASTM D792
	1.48 g/cc	0.0535 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	113 MPa	16400 psi	5 mm/min; ISO 527
	121 MPa	17500 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	113 MPa	16400 psi	5 mm/min; ISO 527
	121 MPa	17500 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	1.5 %	1.5 %	5 mm/min; ISO 527
	1.7 %	1.7 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	1.5 %	1.5 %	5 mm/min; ISO 527
	1.7 %	1.7 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	12.28 GPa	1781 ksi	1 mm/min; ISO 527
	12.8 GPa	1860 ksi	50 mm/min; ASTM D638
Flexural Strength	143 MPa	20700 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Yield Strength	148 MPa	21500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	8.93 GPa	1300 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.970 J/cm	1.82 ft-lb/in	ASTM D256

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	1.00 kJ/m ²	0.476 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	80*10*4; ISO 180/1U
Impact Test	16.0 J	11.8 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	176 °C @Thickness 3.20 mm	349 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	176 °C	349 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	166 °C @Thickness 3.20 mm	331 °F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China