

SABIC Innovative Plastics LNP THERMOCOMP UF004AS PPA (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

Material Notes:

LNP* Thermocomp* UF004AS is a compound based on Polyphthalamide resin containing Glass Fiber. Added features of this material include: Heat Stabilized.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-UF004AS-PPA-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	136 MPa	19700 psi	5 mm/min; ISO 527
Elongation at Break	1.7 %	1.7 %	5 mm/min; ISO 527
Tensile Modulus	7.50 GPa	1090 ksi	1 mm/min; ISO 527
Flexural Strength	178 MPa	25800 psi	2 mm/min; ISO 178
Flexural Modulus	7.00 GPa	1020 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	4.00 kJ/m ²	1.90 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	31.0 Åµm/m-Å°C	17.2 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
CTE, linear, Transverse to Flow	60.0 Åµm/m-Å°C	33.3 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	256 Å°C	493 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China