

## SABIC Innovative Plastics LNP THERMOCOMP UF006H PPA (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

### Material Notes:

LNP\* Thermocomp\* UF006H is a compound based on Polyphthalamide resin containing Glass Fiber.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-UF006H-PPA-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-UF006H-PPA-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in <sup>3</sup>	ISO 1183
	1.53 g/cc	0.0553 lb/in <sup>3</sup>	ASTM D792
Moisture Absorption	0.200 %	0.200 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0037 cm/cm	0.0037 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0077 cm/cm	0.0077 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	208 MPa	30200 psi	ISO 527
	224 MPa	32500 psi	ASTM D638
Tensile Strength, Yield	208 MPa	30200 psi	ISO 527
	224 MPa	32500 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ISO 527
	2.2 %	2.2 %	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ISO 527
	2.2 %	2.2 %	ASTM D638
Tensile Modulus	12.44 GPa	1804 ksi	1 mm/min; ISO 527
	13.1 GPa	1900 ksi	50 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
	294 MPa	42600 psi	ISO 178
Flexural Modulus	11.0 GPa	1600 ksi	ISO 178
	11.03 GPa	1600 ksi	ASTM D790
Izod Impact, Notched	1.06 J/cm	1.99 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.83 J/cm	12.8 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	47.0 kJ/m <sup>2</sup>	22.4 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U
Dart Drop, Total Energy	7.00 J	5.16 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	3.00 J	2.21 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.4 Åµm/m-Å°C	28.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	51.0 Åµm/m-Å°C	28.3 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	28.0 Åµm/m-Å°C	15.6 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	293 Å°C	559 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	305 Å°C	581 Å°F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	282 Å°C	540 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	287 Å°C	549 Å°F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**