

SABIC Innovative Plastics LNP THERMOCOMP ZF004 PPE+PS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

LNP* THERMOCOMP* ZF004 is a compound based on PPE+PS Blend resin containing Glass Fiber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-ZF004-PPEPS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ISO 1183
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ISO 62-1
Linear Mold Shrinkage, Flow	0.0015 cm/cm	0.0015 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	97.0 MPa	14100 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	6.20 GPa	899 ksi	1 mm/min; ISO 527
Flexural Yield Strength	141 MPa	20500 psi	2 mm/min; ISO 178
Flexural Modulus	5.80 GPa	841 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	36.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	20.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
CTE, linear, Transverse to Flow	74.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	41.1 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	135 $\text{Å}^\circ\text{C}$	275 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China