

SABIC Innovative Plastics LNP Thermocomp EF008E PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

LNP* Thermocomp* EF008E is a compound based on Polyetherimide resin containing Glass Fiber. Added features of this material include: Easy Molding. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-Thermocomp-EF008E-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in ³	ASTM D 792
	1.60 g/cc	0.0578 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	50% RH; ASTM D 570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ASTM D 955
	@Time 86400 sec	@Time 24.0 hour	
	0.0030 cm/cm	0.0030 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ASTM D 955
	@Time 86400 sec	@Time 24.0 hour	
	0.0060 cm/cm	0.0060 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	161 MPa	23400 psi	ASTM D 638
	196 MPa	28400 psi	ISO 527
Tensile Strength, Yield	172 MPa	24900 psi	ASTM D 638
	175 MPa	25400 psi	ISO 527
Elongation at Break	4.7 %	4.7 %	ISO 527
	6.6 %	6.6 %	ASTM D 638
Elongation at Yield	5.7 %	5.7 %	ISO 527
	7.5 %	7.5 %	ASTM D 638
Tensile Modulus	10.17 GPa	1475 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric 13.1 GPa	English 1900 ksi	Comments 50 mm/min; ASTM D 638
Flexural Strength	248 MPa	36000 psi	ASTM D 790
Flexural Modulus	11.72 GPa	1700 ksi	ASTM D 790
	15.0 GPa	2180 ksi	ISO 178
Izod Impact, Unnotched	0.110 J/cm @Temperature 23.0 Â°C	0.206 ft-lb/in @Temperature 73.4 Â°F	ASTM D 4812
Izod Impact, Notched (ISO)	7.00 kJ/mÂ² @Temperature 23.0 Â°C	3.33 ft-lb/inÂ² @Temperature 73.4 Â°F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	42.0 kJ/mÂ² @Temperature 23.0 Â°C	20.0 ft-lb/inÂ² @Temperature 73.4 Â°F	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	209 Â°C	408 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	211 Â°C @Thickness 3.20 mm	412 Â°F @Thickness 0.126 in	unannealed; ASTM D 648
Deflection Temperature at 1.8 MPa (264 psi)	206 Â°C	403 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	206 Â°C @Thickness 3.20 mm	403 Â°F @Thickness 0.126 in	unannealed; ASTM D 648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China