

## SABIC Innovative Plastics LNP Thermocomp JX89569 PES

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

### Material Notes:

LNP THERMOCOMP\* JX89569 is a compound based on Polyethersulfone resin containing Glass Fiber. This data was supplied by SABIC-IP for the Americas region.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-Thermocomp-JX89569-PES.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-Thermocomp-JX89569-PES.php)

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in <sup>3</sup>	ASTM D 792
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm @Time 86400 sec	0.0060 - 0.0080 in/in @Time 24.0 hour	ASTM D 955
Linear Mold Shrinkage, Transverse	0.0060 - 0.0080 cm/cm @Time 86400 sec	0.0060 - 0.0080 in/in @Time 24.0 hour	ASTM D 955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	110 MPa	16000 psi	ASTM D 638
Tensile Modulus	26.2 GPa	3800 ksi	50 mm/min; ASTM D 638
Flexural Strength	172 MPa	24900 psi	ASTM D 790
Flexural Modulus	4.68 GPa	679 ksi	ASTM D 790
Izod Impact, Notched	0.530 J/cm @Temperature 23.0 Â°C	0.993 ft-lb/in @Temperature 73.4 Â°F	ASTM D 256
Izod Impact, Unnotched	6.40 J/cm @Temperature 23.0 Â°C	12.0 ft-lb/in @Temperature 73.4 Â°F	ASTM D 4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	208 Â°C @Thickness 3.20 mm	406 Â°F @Thickness 0.126 in	unannealed; ASTM D 648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China