

SABIC Innovative Plastics LNP Thermotuf R1000EI2 PA 66 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

High Impact Nylon 66 compound containing Impact Modifier. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-Thermotuf-R1000EI2-PA-66-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.011 - 0.015 cm/cm	0.011 - 0.015 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.010 - 0.015 cm/cm	0.010 - 0.015 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	ISO 527
Elongation at Break	40 %	40 %	ISO 527
Tensile Modulus	2.20 GPa	319 ksi	1 mm/min; ISO 527
Flexural Strength	70.0 MPa	10200 psi	ISO 178
Flexural Modulus	2.00 GPa	290 ksi	ISO 178
Izod Impact, Notched (ISO)	13.0 kJ/m ²	6.19 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Izod Impact, Unnotched (ISO)	96.0 kJ/m ²	45.7 ft-lb/in ²	80*10*4; ISO 180/1U
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	160 Â°C	320 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	65.0 Â°C	149 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/ Af

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China