

SABIC Innovative Plastics LNP VERTON MV008 PP (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

LNP* VERTON* MV008 is a compound based on Polypropylene resin containing Long Glass. Added features include Chemically Coupled.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-VERTON-MV008-PP-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	120 MPa	17400 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
	2.3 %	2.3 %	Flexural Strain, break, 2 mm/min; ISO 178
Tensile Modulus	9.70 GPa	1410 ksi	1 mm/min; ISO 527
Flexural Yield Strength	175 MPa	25400 psi	2 mm/min; ISO 178
Flexural Modulus	8.60 GPa	1250 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	50.0 kJ/m ²	23.8 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	18.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	10.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
CTE, linear, Transverse to Flow	120 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	66.7 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	160 $\text{Å}^\circ\text{C}$	320 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China