

## SABIC Innovative Plastics LNP VERTON RV00AEX5 PA6.6 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

LNP\* VERTON\* Is a compound based on PA66 resin containing Long Glass Fiber. Added features include: Easy Molding, Heat Stabilized.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-VERTON-RV00AEX5-PA66-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-VERTON-RV00AEX5-PA66-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.90 %	0.90 %	ISO 62-1
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	276 MPa	40000 psi	5 mm/min; ISO 527
Tensile Strength, Yield	276 MPa	40000 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Elongation at Yield	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	17.8 GPa	2580 ksi	1 mm/min; ISO 527
Flexural Yield Strength	366 MPa	53100 psi	2 mm/min; ISO 178
Flexural Modulus	15.0 GPa	2180 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	45.0 kJ/m <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	90.0 kJ/m <sup>2</sup>	42.8 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	259 Â°C	498 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	256 Â°C	493 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

UL RTI Electrical Thermal Properties	105 Â°C Metric	221 Â°F English	UL 746B Comments
UL RTI, Mechanical with Impact	110 Â°C	230 Â°F	UL 746B
UL RTI, Mechanical without Impact	110 Â°C	230 Â°F	UL 746B
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	UL 94

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China