

SABIC Innovative Plastics LNP VERTON RV00AXX9 PA 66 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LNP* VERTON* RV00AXX9 is a compound based on PA 66 resin containing Long Glass Fiber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-VERTON-RV00AXX9-PA-66-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.57 g/cc	0.0567 lb/in ³	ISO 1183
Moisture Absorption	0.800 %	0.800 %	23°C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0024 cm/cm @Time 86400 sec	0.0024 in/in @Time 24.0 hour	ISO 294
Linear Mold Shrinkage, Transverse	0.0079 cm/cm @Time 86400 sec	0.0079 in/in @Time 24.0 hour	ISO 294

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	268 MPa	38900 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	17.6 GPa	2550 ksi	1 mm/min; ISO 527
Flexural Strength	405 MPa	58700 psi	2 mm/min; ISO 178
Flexural Modulus	15.5 GPa	2250 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	35.0 kJ/m ²	16.7 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	100 kJ/m ²	47.6 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	24.0 μm/m-°C @Temperature 23.0 - 60.0 °C	13.3 μin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2
CTE, linear, Transverse to Flow	54.0 μm/m-°C @Temperature 23.0 - 60.0 °C	30.0 μin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	265 °C	509 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf

Thermal Properties (at 1.8 MPa (264 psi))	Metric	English	Comments
UL RTI, Electrical	105 °C	221 °F	UL 746B
UL RTI, Mechanical with Impact	110 °C	230 °F	UL 746B
UL RTI, Mechanical without Impact	110 °C	230 °F	UL 746B
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	UL 94

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 600 V	>= 600 V	IEC 60112
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China