

SABIC Innovative Plastics Lexan® 223 PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

17.5 MFR, for small, intricate parts. Improved flame retardance. UV stabilized. This data was supplied by SABIC-IP for the Americas region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-223-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D 792
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D 570
Moisture Absorption at Equilibrium	0.35 % @Temperature 23.0 °C	0.35 % @Temperature 73.4 °F	ASTM D 570
	0.58 % @Temperature 100 °C	0.58 % @Temperature 212 °F	ASTM D 570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	17.5 g/10 min @Load 1.20 kg, Temperature 300 °C	17.5 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D 785
Hardness, Rockwell R	118	118	ASTM D 785
Tensile Strength at Break	65.0 MPa	9430 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D 638
Elongation at Break	110 %	110 %	Type I, 50 mm/min; ASTM D 638
Elongation at Yield	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D 638
Flexural Yield Strength	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D 790

Mechanical Properties	Metric	English	Comments
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched	32.04 J/cm @Temperature 23.0 °C	60.02 ft-lb/in @Temperature 73.4 °F	ASTM D 4812
Tensile Impact Strength	546 kJ/m ²	260 ft-lb/in ²	Type S; ASTM D 1822
Dart Drop, Total Energy	169 J @Temperature 23.0 °C	125 ft-lb @Temperature 73.4 °F	ASTM D 3029
Taber Abrasion, mg/1000 Cycles	10 @Load 1.00 kg	10 @Load 2.20 lb	CS-17; ASTM D 1044

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 μm/m-°C @Temperature -40.0 - 95.0 °C	38.0 μin/in-°F @Temperature -40.0 - 203 °F	ASTM E 831
Specific Heat Capacity	1.25 J/g-°C	0.299 BTU/lb-°F	ASTM C 351
Thermal Conductivity	0.250 W/m-K	1.74 BTU-in/hr-ft ² -°F	ASTM C 177
Deflection Temperature at 0.46 MPa (66 psi)	137 °C @Thickness 6.40 mm	279 °F @Thickness 0.252 in	unannealed; ASTM D 648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C @Thickness 6.40 mm	270 °F @Thickness 0.252 in	unannealed; ASTM D 648
Vicat Softening Point	154 °C	309 °F	Rate B/50; ASTM D 1525
UL RTI, Electrical	100 °C	212 °F	UL 746B
UL RTI, Mechanical with Impact	100 °C	212 °F	UL 746B
UL RTI, Mechanical without Impact	100 °C	212 °F	UL 746B
Flammability, UL94	V-2 @Thickness 1.47 mm	V-2 @Thickness 0.0579 in	UL 94
	V-0 @Thickness 5.99 mm	V-0 @Thickness 0.236 in	UL 94

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D 542
	1.0 %	1.0 %	

Haze Optical Properties	Metric @ Thickness 2.54 mm	English @ Thickness 0.100 in	ASTM D 1003 Comments
Transmission, Visible	88 % @Thickness 2.54 mm	88 % @Thickness 0.100 in	ASTM D 1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	ASTM D 257
Dielectric Constant	2.96	2.96	ASTM D 150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	3.17	3.17	ASTM D 150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	14.9 kV/mm	378 kV/in	in air; ASTM D 149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.00090	0.00090	ASTM D 150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dissipation Factor	0.010	0.010	ASTM D 150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	250 - 400 V	250 - 400 V	PLC code 2; UL 746A
Hot Wire Ignition, HWI	7.0 - 15 sec	7.0 - 15 sec	PLC code 4; UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	surface, PLC code 1; UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	PLC code 2; UL 746A

Descriptive Properties	Value	Comments
UV-light, water exposure/immersion	F1	UL 746C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China