

## SABIC Innovative Plastics Lexan® 3412R PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

LEXAN 3412R is a high viscosity, 20% glass reinforced grade. It offers excellent flame retardancy and is especially designed for applications requiring high rigidity together with high heat.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-3412R-PC-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-3412R-PC-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.120 %	0.120 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.29 %	0.29 %	ISO 62
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	on Tensile Bar; SABIC Method
Melt Index of Compound	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	125 MPa	18100 psi	ISO 2039-1
Tensile Strength at Break	90.0 MPa	13100 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	6.00 GPa	870 ksi	1 mm/min; ISO 527
Flexural Strength	120 MPa	17400 psi	2 mm/min; ISO 178
Flexural Modulus	5.50 GPa	798 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	6.00 kJ/m <sup>2</sup> @Temperature -30.0 °C	2.86 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	35.0 kJ/m <sup>2</sup>	16.7 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1U
	35.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	16.7 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*3; ISO 180/1U
Charpy Impact Unnotched	4.00 J/cm <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eU

Mechanical Properties	4.00 J/cm <sup>2</sup> Metric	19.0 ft-lb/in <sup>2</sup> English	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.600 J/cm <sup>2</sup>	2.86 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	0.900 J/cm <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	ISO 179/2C
	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Taber Abrasion, mg/1000 Cycles	17	17	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 μm/m-°C	16.7 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ft <sup>2</sup> -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	144 °C	291 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	139 °C	282 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	145 °C	293 °F	Rate B/120; ISO 306
	147 °C	297 °F	Rate B/50; ISO 306
	155 °C	311 °F	Rate A/50; ISO 306
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	125 °C	257 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B
Flammability, UL94	V-0	V-0	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Oxygen Index	37 %	37 %	ISO 4589
Glow Wire Test	850 °C	1560 °F	IEC 60695-2-12
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	$\geq 1.00\text{e}+15$ ohm-cm Metric	$\geq 1.00\text{e}+15$ ohm-cm English	IEC 60093 Comments
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	ROA; IEC 60093
Dielectric Constant	2.9	2.9	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.0	3.0	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	16.0 kV/mm	406 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
	20.0 kV/mm	508 kV/in	short time; IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	25.0 kV/mm	635 kV/in	in oil; IEC 60243-1
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	33.0 kV/mm	838 kV/in	in oil; IEC 60243-1
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	150 V	150 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2
Haze, 2.54 mm	NA%	ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China