

## SABIC Innovative Plastics Lexan® 3414R PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

40% GR, provides improved mechanical properties and UL94V-1 rated at 0.058". Internal mold release added.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-3414R-PC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-3414R-PC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Density	1.522 g/cc	0.05499 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.12 % @Time 86400 sec	0.12 % @Time 24.0 hour	ASTM D570
Moisture Absorption at Equilibrium	0.23 %	0.23 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm @Thickness 3.20 mm	0.0010 - 0.0020 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	12.6 g/10 min @Load 5.00 kg, Temperature 300 °C	12.6 g/10 min @Load 11.0 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	93	93	ASTM D785
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength at Break	158 MPa	22900 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Flexural Yield Strength	186 MPa	27000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	9.65 GPa	1400 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.33 J/cm	2.49 ft-lb/in	ASTM D256
Izod Impact, Unnotched	12.81 J/cm	24.00 ft-lb/in	ASTM D4812
Tensile Impact Strength	67.0 kJ/m <sup>2</sup>	31.9 ft-lb/in <sup>2</sup>	Type S; ASTM D1822
Dart Drop, Total Energy	6.00 J	4.43 ft-lb	ASTM D3029
Taber Abrasion, mg/1000 Cycles	32	32	CS-17, 1 kg; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	16.2 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	9.00 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E 831
	@Temperature -40.0 - 95.0 $^{\circ}\text{C}$	@Temperature -40.0 - 203 $^{\circ}\text{F}$	
Specific Heat Capacity	1.04 J/g- $^{\circ}\text{C}$	0.249 BTU/lb- $^{\circ}\text{F}$	ASTM C351
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	154 $^{\circ}\text{C}$	309 $^{\circ}\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	146 $^{\circ}\text{C}$	295 $^{\circ}\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	165 $^{\circ}\text{C}$	329 $^{\circ}\text{F}$	Rate B/50; ASTM D1525
UL RTI, Electrical	130 $^{\circ}\text{C}$	266 $^{\circ}\text{F}$	UL 746B
UL RTI, Mechanical with Impact	130 $^{\circ}\text{C}$	266 $^{\circ}\text{F}$	UL 746B
UL RTI, Mechanical without Impact	130 $^{\circ}\text{C}$	266 $^{\circ}\text{F}$	UL 746B
Flammability, UL94	V-1	V-1	UL 94
	@Thickness 1.11 mm	@Thickness 0.0437 in	
	V-0	V-0	UL 94
	@Thickness 2.99 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+17$ ohm-cm	$\geq 1.00\text{e}+17$ ohm-cm	ASTM D257
Dielectric Constant	3.48	3.48	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.53	3.53	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	17.7 kV/mm	450 kV/in	in air; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0013	0.0013	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.0067	0.0067	

Electrical Properties	Metric @ Frequency 1.00e+6 Hz	English @ Frequency 1.00e+6 Hz	Comments ASTM D750
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495
Comparative Tracking Index	100 - 175 V	100 - 175 V	UL 746A
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	UL 746A
High Amp Arc Ignition, HAI	0.00 - 15 arcs	0.00 - 15 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

Descriptive Properties	Value	Comments
Specific Volume	0.65cm <sup>3</sup> /g	ASTM D792

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China