

## SABIC Innovative Plastics Lexan® 4401R PPC+PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polyphthalate Carbonate

### Material Notes:

LEXAN 4401R is a high heat resistant poly(ester)carbonate injection molding resin. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-4401R-PPCPC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-4401R-PPCPC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption at Equilibrium	0.35 %	0.35 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.16 % @Temperature 23.0 °C	0.16 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	on tensile bar; SABIC Method
	0.0060 - 0.0080 cm/cm @Thickness 3.20 mm	0.0060 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.00 - 0.0020 cm/cm @Thickness 3.20 mm	0.00 - 0.0020 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238
	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm <sup>3</sup> /10 min] Melt Volume Rate; ISO 1133
	29 g/10 min @Load 2.16 kg, Temperature 330 °C	29 g/10 min @Load 4.76 lb, Temperature 626 °F	[cm <sup>3</sup> /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	50 mm/min; ISO 527
	70.0 MPa	10200 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
	66.0 MPa	9570 psi	Type I, 50 mm/min; ASTM D 638

Mechanical Properties	Metric	English	Comments
Elongation at Break	85 %	85 %	Type I, 50 mm/min; ASTM D 638
	85 %	85 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D 638
Tensile Modulus	2.10 GPa	305 ksi	5 mm/min; ASTM D 638
	2.15 GPa	312 ksi	1 mm/min; ISO 527
Flexural Yield Strength	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D 790
	100 MPa	14500 psi	2 mm/min; ISO 178
Flexural Modulus	2.20 GPa	319 ksi	1.3 mm/min, 50 mm span; ASTM D 790
	2.30 GPa	334 ksi	2 mm/min; ISO 178
Izod Impact, Notched	6.00 J/cm	11.2 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched	NB	NB	ASTM D 4812
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	11.0 kJ/m <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	53.0 kJ/m <sup>2</sup>	25.2 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.30 J/cm <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	5.40 J/cm <sup>2</sup>	25.7 ft-lb/in <sup>2</sup>	V-notch Edgew 80*10*3 sp=62mm;

Mechanical Properties	Metric @ Temperature 23.0 °C	English @ Temperature 73.4 °F	ISO 179/1eA Comments
Impact Test	120 J @Temperature 23.0 °C	88.5 ft-lb @Temperature 73.4 °F	Instrumented Impact Total Energy; ASTM D 3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	148 °C @Thickness 3.20 mm	298 °F @Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	137 °C	279 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	142 °C @Thickness 3.20 mm	288 °F @Thickness 0.126 in	
Vicat Softening Point	155 °C	311 °F	Rate B/50; ISO 306
	157 °C	315 °F	Rate B/120; ISO 306
	166 °C	331 °F	Rate B/50; ASTM D 1525

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	pass	IEC 60695-10-2

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China