

**SABIC Innovative Plastics Lexan® 9945A PC**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

Lexan® resin 9945A Polycarbonate (PC) is a non-filled, injection moldable grade. This non-chlorinated, non-brominated PC has an UL-94 V0 rating at 1.8 mm. Lexan resin 9945A is available in clear transparent only and is a general-purpose resin intended for thin wall applications.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-9945A-PC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-9945A-PC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	65.0 MPa	9430 psi	50 mm/min; ISO 527
	66.0 MPa	9570 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	63.0 MPa	9140 psi	50 mm/min; ISO 527
	64.0 MPa	9280 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	100 %	100 %	50 mm/min; ISO 527
	120 %	120 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	102 MPa	14800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.45 GPa	355 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.20 J/cm	15.4 ft-lb/in	ASTM D256
	1.10 J/cm @Temperature -30.0 °C	2.06 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Notched (ISO)	70.0 kJ/m <sup>2</sup>	33.3 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	12.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	5.71 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	80*10*3; ISO 180/1U
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	7.30 J/cm <sup>2</sup>	34.7 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.40 J/cm <sup>2</sup> @Temperature -30.0 °C	6.66 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	79.0 J	58.3 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.0 µm/m-°C	37.8 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	

Thermal Properties	Metric /m-°C	English /in-°F	Comments
CTE, linear, Transverse to Flow	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
	73.0 μm/m-°C @Temperature -40.0 - 40.0 °C	40.6 μin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft <sup>2</sup> -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	136 °C	277 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	138 °C @Thickness 3.20 mm	280 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	127 °C @Thickness 3.20 mm	261 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	141 °C	286 °F	Rate B/50; ISO 306
	142 °C	288 °F	Rate B/120; ISO 306
	143 °C	289 °F	Rate B/50; ASTM D1525
Flammability, UL94	V-2 @Thickness 0.800 mm	V-2 @Thickness 0.0315 in	UL 94
	V-0 @Thickness 1.80 mm	V-0 @Thickness 0.0709 in	UL 94
Oxygen Index	35 %	35 %	ISO 4589
Glow Wire Test	850 °C	1560 °F	IEC 60695-2-13
	850 °C	1560 °F	IEC 60695-2-13
	960 °C @Thickness 1.00 mm	1760 °F @Thickness 0.0394 in	IEC 60695-2-12

Optical Properties	Metric	English	Comments
Haze	1.0 %	1.0 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	2.7	2.7	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	225 V	225 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China