

**SABIC Innovative Plastics Lexan® BM5225X PC (Asia Pacific)**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

BM5225X resin is a mineral filled grade featuring of high modulus, good flow and ductility, low warpage. It is of non-Br & non-Cl flame retardant systems intended to meet thin wall flame resistance and various environmental requirements.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-BM5225X-PC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-BM5225X-PC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0030 cm/cm @Thickness 3.20 mm	0.0020 - 0.0030 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 260 °C	12 g/10 min @Load 4.76 lb, Temperature 500 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
Tensile Strength at Break	30.0 MPa	4350 psi	5 mm/min; ISO 527
	34.0 MPa	4930 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	55.0 MPa	7980 psi	Type I, 5 mm/min; ASTM D638
	56.0 MPa	8120 psi	5 mm/min; ISO 527
Elongation at Break	6.0 %	6.0 %	5 mm/min; ISO 527
	15 %	15 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
	3.0 %	3.0 %	5 mm/min; ISO 527
Tensile Modulus	5.57 GPa	808 ksi	1 mm/min; ISO 527
	5.85 GPa	848 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	98.0 MPa	14200 psi	1.3 mm/min, 50 mm span; ASTM D790
	98.0 MPa	14200 psi	2 mm/min; ISO 178

Mechanical Properties	Metric	English	Comments
	6.01 GPa	872 ksi	1.3 mm/min, 50 mm span; ASTM D790
	6.15 GPa	892 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.900 J/cm	1.69 ft-lb/in	ASTM D256
	0.500 J/cm	0.937 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	29.0 J	21.4 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	34.0 µm/m-°C	18.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
CTE, linear, Transverse to Flow	72.0 µm/m-°C	40.0 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	87.0 °C	189 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	85.0 °C	185 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	98.0 °C	208 °F	Rate B/50; ASTM D1525
Flammability, UL94	V-1	V-1	UL 94
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	V-0	V-0	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	5VB	5VB	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China